

Glove Compatibility Chart

Chemical	Silver Shield (4 Mil)			Viton (9 Mil)			Butyl (17 Mil)			Nitrile (11 Mil)			Neoprene (22 Mil)			PVC (20 MIL)		
	D	BT	PR	D	BT	PR	D	BT	PR	D	BT	PR	D	BT	PR	D	BT	PR
Acetaldehyde	E	>6h	ND	P	0m	281.9	E	9.6	0.07	F	4m	161	E	21m	18	ID	ID	ID
Acetone	E	>6h	ND	P	ID	ID	E	>17h	ND	P	ID	ID	E	12m	35	P	>1m	>>
Acetonitrile	E	>8h	ND	ID	ID	ID	E	>8h	ND	ID	ID	ID	E	40m	7	ID	ID	ID
Acrylic Acid	ID	ID	ID	G	5.9h	0.23	E	>8h	ND	F	ID	ID	ID	ID	ID	ID	ID	ID
Acrylonitrile	E	ID	ID	F	1m	176	G	3.1h	<0.01	P	3m	176	ID	ID	ID	ID	ID	ID
Aldehyde	E	>6h	ND	P	0m	281.9	E	9.5h	0.07	P	4	161	ID	ID	ID	ID	ID	ID
Aniline	E	>8h	ID	G	10m	18.7	F	>8h	ND	P	1.1h	45	E	>8h	ND	G	>8h	ND
Benzaldehyde	ID	ID	ID	F	9.9h	4	E	9h	ND	P	ID	ID	ID	ID	ID	ID	ID	ID
Benzene	E	>8h	ND	G	6h	0.012	P	31m	32.3	P	ID	ID	ID	16m	133	ID	2m	250
Benzoyl Chloride	ID	ID	ID	E	>8h	ND	F	6.2h	16.6	P	ID	ID	ID	ID	ID	ID	ID	ID
Bromobenzene	E	ID	ID	E	8h	ND	P	32m	39.8	P	13m	9.1	ID	ID	ID	ID	ID	ID
Butyl Acetate	E	>6h	ND	P	ID	ID	G	1.9h	7.61	P	29m	54.4	ID	52m	53	ID	ID	ID
p-t Butyltoluene	E	>8h	ND	E	>8h	ND	G	1.7h	8	P	ID	ID	ID	ID	ID	ID	ID	ID
Butyraldehyde	E	ID	ID	P	54m	9	E	>15h	ND	P	ID	ID	ID	ID	ID	ID	ID	ID
Carbon Disulfide	G	>8h	ND	E	>8h	ND	P	7m	98	P	1m	51	ID	ID	ID	ID	ID	ID
Carbon Tetrachloride	E	>6h	ND	E	>13h	ND	P	ID	ID	G	3.4h	5	F	31m	252	ID	ID	ID
Cellosolve	G	>6h	ND	F	ID	ID	G	ID	ID	P	ID	ID	E	5.9h	3	ID	ID	ID
Chlorobenzene	E	ID	ID	E	>8h	ND	P	35m	308	P	ID	ID	ID	ID	ID	ID	ID	ID
Chloroform	P	10m	O.OO9	E	9.5h	0.46	P	ID	ID	P	4m	352	P	12m	220	ID	ID	ID
Chloronaphthalene	E	>8h	ND	E	>16h	ND	P	ID	ID	P	2.9h	>1.3	ID	ID	ID	ID	ID	ID
Chloroprene	ID	ID	ID	ID	>8h	ND	P	28m	18	ID	ID	ID	ID	ID	ID	ID	ID	ID
Cyclohexane	E	>6h	ND	E	>7h	ND	P	1.1h	20.3	P	ID	ID	E	2.7h	7	ID	16m	17

Glove Compatibility Chart

	Silver Shield (4 Mil)			Viton (9 Mil)			Butyl (17 Mil)			Nitrile (11 Mil)			Neoprene (22 Mil)			PVC (20 MIL)		
Cyclohexanol	E	>6h	ND	E	>8h	ND	E	>11h	ND	E	>16h	ND	ID	ID	ID	ID	ID	ID
Cyclohexanone	E	>6h	ND	P	29m	86.3	E	>16h	ND	P	ID	ID	ID	ID	ID	ID	ID	ID
Dibutylphthalate	E	>6h	ND	E	>8h	ND	E	>16h	ND	E	>16h	ND	ID	ID	ID	ID	ID	ID
1,1-Dichloroethane	ID	2.4h	6	G	1.5h	31	ID	ID	ID	P	ID	ID	ID	ID	ID	ID	ID	ID
1,2-Dichloroethane	E	>6h	ND	E	6.9	0.81	P	2h	53	P	8m	311	P	33m	247	ID	ID	ID
Diethylamine	E	>8h	ND	P	35m	852	P	47m	46	F	ID	ID	ID	ID	ID	ID	ID	ID
Diethylaminoethanol	E	ID	ID	E	>8h	ND	E	>8h	ND	E	>8h	ND	ID	ID	ID	ID	ID	ID
1,4-Diethylene Dioxide	ID	>8h	ND	P	23m	26.8	E	>20h	ND	P	28m	77.1	ID	28m	62	ID	8m	250
Diethylenetriamine	ID	ID	ID	E	>8h	ND	E	>8h	ND	P	ID	ID	ID	ID	ID	ID	ID	ID
Diisobutyl Ketone 80%	E	>6h	ND	F	1.2h	90.6	G	3.3h	41.2	F	3h	48.9	ID	ID	ID	ID	ID	ID
Dimethyl Acetamide	ID	1.5h	0.728	P	25m	3	ID	>8h	ND	ID	ID	ID	ID	ID	ID	ID	ID	ID
Dimethyl Formamide	E	>8h	ND	P	8m	6.5	E	>8h	ND	F	1m	>15	ID	ID	ID	ID	ID	ID
Dimethylsulfoxide	G	ID	ID	F	1.5h	5	E	>8h	ND	F	ID	ID	ID	ID	ID	ID	ID	ID
Dioxane	E	>8h	ND	F	23m	26.8	E	>20h	ND	P	28m	77.1	ID	28m	62	ID	8m	250
Divinyl Benzene	E	>8h	ND	E	>17h	ND	F	2.2h	238	P	ID	ID	ID	ID	ID	ID	ID	ID
Epichlorohydrin	ID	ID	ID	P	2h	4	G	>8h	ND	P	ID	ID	ID	ID	ID	ID	ID	ID
Ether	ID	>6h	ND	P	12m	21.5	P	8m	92.2	P	14m	21.8	ID	ID	ID	ID	ID	ID
Ethyl Acetate	E	>6h	ND	P	ID	ID	G	7.6h	3.4	P	8m	145	G	34m	178	ID	ID	ID
Ethyl Ether	ID	>6h	ND	P	12m	21.5	P	8m	92.2	P	14m	21.8	E	18m	51	ID	ID	ID
Ethylamine 70%	E	47m	7.64	P	ID	ID	E	>12h	ND	F	1.1h	30.1	ID	ID	ID	ID	ID	ID
Ethylene dibromide	E	ID	ID	E	>8h	ND	F	3.3h	6	P	ID	ID	ID	ID	ID	ID	ID	ID
Formaldehyde 37%	E	>6h	ND	E	>16h	ND	E	16h	ND	E	>21h	ND	E	>8h	ND	G	8h	ND
Furan	ID	ID	ID	P	20m	23	P	1.3h	10	P	ID	ID	ID	ID	ID	ID	ID	ID
Furfural	E	>8h	ND	F	3.6h	14.8	E	>16h	ND	P	28m	265	ID	ID	ID	ID	ID	ID

Glove Compatibility Chart

	Silver Shield (4 Mil)			Viton (9 Mil)			Butyl (17 Mil)			Nitrile (11 Mil)			Neoprene (22 Mil)			PVC (20 MIL)		
Glutaraldehyde	E	ID	ID	E	>8h	ND	E	>8h	ND	P	ID	ID	ID	ID	ID	ID	ID	ID
n-Hexane	E	>6h	ND	ID	>11h	ND	P	ID	ID	E	ID	ID	E	39m	5	ID	ID	ID
Hydrazine 70%	G	>6h	ND	P	ID	ID	E	>8h	ND	G	>8h	ND	E	>8h	ND	E	8h	ND
Hydrochloric Acid 37%	E	>6h	ND	E	ID	ID	E	ID	ID	P	ID	ID	E	>8h	ND	E	>8h	ND
Hydrofluoric Acid 50%	G	>6h	ND	G	ID	ID	F	ID	ID	P	ID	ID	E	>8h	ND	E	1.8h	0
Isobutyl Alcohol	E	ID	ID	E	>8h	ND	E	>8h	ND	G	>8h	ND	ID	ID	ID	ID	ID	ID
Isobutyraldehyde	E	ID	ID	P	4m	11.5	E	>8h	ND	P	ID	ID	ID	ID	ID	ID	ID	ID
Methacrylic Acid	ID	ID	ID	F	>8h	ND	G	>8h	ND	P	1.7h	23	ID	ID	ID	ID	ID	ID
Methacrylonitrile	E	ID	ID	F	4m	462	G	6.8h	0.001	P	7m	560	ID	ID	ID	ID	ID	ID
Methyl Chloroform	ID	>6h	ND	E	>15h	ND	P	ID	ID	P	41m	76.4	P	27m	197	ID	ID	ID
Methyl Cyanide	ID	>8h	ND	ID	ID	ID	E	>8h	ND	ID	ID	ID	E	40m	7	ID	ID	ID
Methyl Ethyl Ketone	E	>24h	ND	P	ID	ID	E	>8h	ND	P	ID	ID	G	22m	155	ID	1m	>>
Methyl Isocyanate	ID	ID	ID	P	4m	121	P	1.1h	9	P	ID	ID	ID	ID	ID	ID	ID	ID
Methylamine 40%	F	1.9h	2	E	>16h	ND	E	>15h	ND	G	>8h	ND	ID	ID	ID	ID	ID	ID
Methylene Chloride	G	>8h	ND	F	1h	7.32	P	24m	133	P	4m	766	F	6m	239	ID	ID	ID
Methylene Dianiline	E	>24h	ND	E	>8h	ND	E	>24h	ND	F	ID	ID	ID	ID	ID	ID	ID	ID
Methylene Dichloride	ID	1.9h	0.002	G	1.9h	7.32	P	ID	ID	P	4m	766	ID	ID	ID	ID	ID	ID
Morpholine	E	>8h	ND	G	ID	97	E	>16h	ND	P	48m	206	ID	ID	ID	ID	ID	ID
Nitric Acid, 3 Molar	E	>6h	ND	G	>8h	ID	F	ID	ID	P	ID	ID	E	>8h	ND	E	1.9h	0
Nitrobenzene	E	>8h	ND	E	21m	ND	E	>23	ND	F	33m	1.7	G	1h	20	ID	ID	ID
Nitropropane	E	>8h	ND	P	>8h	26.1	E	>8h	ND	P	16m	29.5	ID	ID	ID	ID	ID	ID
Oxalic Acid	E	>8h	ND	E	>8h	ND	E	>8h	ND	G	ID	ID	ID	ID	ID	ID	ID	ID
PCB, Aroclor 1254 50%	E	>8h	ND	E	>13h	ND	P	ID	ID	F	ID	ID	ID	ID	ID	ID	ID	ID
Pentachlorophenol 1% (2)	E	>8h	ND	ID	>8h	ND	P	ID	ID	E	>13h	ND	ID	8h	ND	ID	ID	ID

Glove Compatibility Chart

	Silver Shield (4 Mil)			Viton (9 Mil)			Butyl (17 Mil)			Nitrile (11 Mil)			Neoprene (22 Mil)			PVC (20 MIL)		
n-Pentane	E	>6h	ND	E	>17h	ND	P	ID	ID	E	ID	ID	ID	38m	3	ID	9m	17
Perchloroethylene	E	>6h	ND	E	>15h	ND	P	ID	ID	F	>1.3h	5.5	ID	28m	75.5	ID	ID	ID
Phenol 85%, water sat	G	>6h	ND	E	ID	ND	E	>20h	ND	P	39m	>1500	E	>8h	ND	ID	32m	13
Propyl Acetate	E	>6h	ND	P	ID	ID	G	2.7h	2.86	P	17m	72.5	ID	ID	ID	ID	ID	ID
Propylenediamine	ID	ID	ID	E	38m	ND	E	>8h	ND	F	ID	ID	ID	ID	ID	ID	ID	ID
Pyridine	ID	ID	ID	P	ID	74	G	>8h	ND	P	ID	ID	ID	28m	117	ID	1m	>>
Red Fuming Nitric Acid	P	35m	ID	P	ID	ID	P	ID	ID	P	ID	ID	ID	ID	ID	ID	ID	ID
Sodium Hydroxide 50%	E	>6h	ND	G	ID	ID	E	ID	ID	G	ID	ID	E	>6.7h	ND	E	8h	ND
Styrene	G	>4h	ND	G	ID	ID	P	ID	ID	P	ID	ID	ID	ID	40	ID	27m	40
Sulfuric Acid, 3 Molar	E	>6h	ND	E	ID	ID	G	ID	ID	P	ID	ID	E	>6.7h	ND	E	>8h	ND
Tetrachloroethylene	E	>6h	ND	E	>17h	ND	P	ID	ID	F	1.3h	5.5	ID	28m	75.5	ID	ID	ID
Tetraethylenepentamine	ID	ID	ND	E	>8h	ND	E	>8h	ND	F	ID	ID	ID	ID	ID	ID	ID	ID
Tetrafluoroethylene	E	ID	ID	E	>8h	ND	E	>8h	ND	ID	ID	ID	ID	ID	ID	ID	ID	ID
Tetrahydrofuran	E	>8h	ND	P	4m	327	F	31m	112	P	4m	167	P	11m	671	ID	1m	>>
Thiophene	ID	>6h	ND	E	>8h	ND	P	1.8h	17	P	ID	ID	ID	ID	ID	ID	ID	ID
Toluene	E	>6h	ND	E	>16h	ND	F	21m	22.1	P	11m	68.1	ID	14m	576	ID	3m	350
Toluene Diisocyanate	E	>8h	ND	E	>16h	ND	E	>8h	ND	G	3.7h	1.8	ID	ID	ID	G	>6.7	ND
Trichloroethane	E	>6h	ND	G	7.4h	0.24	P	18m	550	P	8m	283	ID	11m	881	ID	ID	ID
1,1,1 Trichloroethane	E	>6h	ND	E	>15h	ND	P	ID	ID	F	41m	76.4	P	27m	197	ID	ID	ID
1,1,2 Trichloroethane	ID	ID	ID	E	>8h	ND	P	5.7h	7	P	ID	ID	ID	ID	ID	ID	ID	ID
Triethylamine	ID	ID	ID	E	>8h	ND	P	ID	ID	E	>8h	ND	ID	ID	ID	ID	ID	ID
Vinyl Chloride	E	>8h	ND	G	4.4h	0.098	P	ID	ID	G	5.7h	0.14	ID	ID	ID	ID	ID	ID
Xylene	E	>24h	ND	E	>8h	ND	P	ID	ID	P	ID	ID	ID	23m	135	ID	4m	383

Glove Compatibility Chart

	Silver Shield (4 Mil)	Viton (9 Mil)	Butyl (17 Mil)	Nitrile (11 Mil)	Neoprene (22 Mil)	PVC (20 MIL)
--	--------------------------	------------------	-------------------	---------------------	----------------------	-----------------

(1)The data for Silver Shield™, Viton™, Butyl and Nitrile gloves were provided by Siebe North Inc, Charleston, SC; information on Neoprene and Polyvinyl Chloride (PVC) gloves were supplied by Pioneer Industrial Products, Williard, OH.

(2)In Kerosene

E=Excellent; **G**=Good; **F**=Fair; **P**=Poor; **ND**=None detected; **ID**=Insufficient Data; **D**=Degradation; **BT**=Breakthrough, amount of elapsed time after initial exposure before the chemical can be analytically detected on the inside surface of the glove; **PR**=Permeation Rate is expressed in mg/m²/sec. PR can be used for estimating glove thickness required; for a given material, thicker is more resistant.

Note: Silver Shield gloves may be worn as liners under other glove types to enhance protection.

Table used by permission of Van Nostrand Reinhold publishing.